

بسم الله الرحمن الرحيم



International University of Africa

Deanship of Graduate Studies

Faculty of Pure and Applied Sciences

Department of Applied Chemistry

**Investigation of the Utilization of Local Fuller Earth for
Treatment of Vegetable oils**

A dissertation Submitted in Partial Fulfillment of the Requirements
for the degree of M.Sc., in Industrial Chemistry

Prepared by:

Abeer Abdelmawgoud Abdelkarim Idris

B.S.c. Laboratory Technology (Chemistry)

H.D. Industrial Chemistry

Supervised by:

Dr. Salma Omer Alhag Ali

Khartoum – Sudan

Mar. 2016

الآية

قال تعالى :

(إنا خلقناه من طين لازب)

" ١١ الصافات "

قال تعالى :

(أني أخلق لكم من الطين كهيئة الطير)

" ٤٩ آل عمران "

DEDICATION

It is my pleasure and great honor to dedicate this humble research with all amiability and respect to:

Who is suffering day after day, and bears pressures, troubles and obstacles.

Who fought all difficulties, and shines our life.

(Dear father)

To whom treats our hearts, who draws the smiles in our faces and the happiness on our life, bears starving to feed us and cold to warm us.

(Great mother)

The pride supports kindness and real love, for whom we can't live without them, (Lovely sisters and dear brothers)

To all who taught, support and share with us everything they know.

Acknowledgement

All praises are due to ALLA the creator of heavens and earth and whatever within them, who the one taught mankind to use pen and made knowledge and science in highest degree.

Firstly will start with simple expressive words and phrases full of feeling to cover whole universe by beauty and happiness to my beloved parents.

Then all thanks to our staff for what they have given us of science and knowledge,

Also thanks and appreciation to:

International university of Africa and very special thanks to,

Dr. Salma Omer Alhag Ali

"For making this project success by her efforts, opinions and time"

And thanks to all who contributed to reach this humble step,

Those who supported and gave me their thoughts, efforts and time.

CONTENTS

No.	Topic	Page
I	الآية	I
II	Dedication	II
III	Acknowledgment	III
IV	Contents	IV
V	List of figures	VI
VI	List of tables	VII
VII	Abstract	VIII
VIII	ملخص البحث	IX
1	Chapter One: Introduction	
1.1	Introduction	1
1.1.1	History of the fuller's earth industry in the United States	1
1.1.2	Definition of fuller earth	2
1.1.3	Bleaching earth	2
1.1.4	Objective of the study	4
2	Chapter Tow: Literature Review	
2.1	Chemical composition of fuller's earth	5
2.2	Occurrence of fuller's earth in the United states	5
2.3	Properties of fuller's earth	7
2.4	Mining of fullers earth	10
2.5	Milling practice	11
2.6	Crushing and drying	11
2.7	Bolting the ground product	14
2.8	Relative proportions of product according to size	14
2.9	Use of fullers earth	15
2.10	Bleaching of edible oils with fullers earth	16
2.11	Proportion of earth required for different oils	16
2.12	Mill practice	16
2.13	Effect of fine grinding	17
2.14	Revivifying the used earth	18
2.15	Vegetable oils	18
2.15.1	Properties	19
2.15.2	Biological value	20
2.15.3	Preparation	20

2.15.4	Uses	22
2.15.5	Refining	22
2.16	Peanut oil	23
2.16.1	History	23
2.16.2	Nutritional content	23
2.16.3	Biodiesel	26
	Chapter Three: Material And Methods	
3.1	Preparation of clay sample	27
3.1.1	Sampling	28
3.1.2	Chemicals and materials	28
3.1.3	Equipment's	28
3.2	Methods	29
3.2.1	Clay preparation	29
3.2.2	Acid activation of the clay samples	30
3.2.3	Adsorption experiment	30
3.2.4	Bleaching/adsorption efficiency determination	32
3.2.5	Laboratory method of determining filtering properties	33
3.2.6	Removing of taste and odor from edible oils	34
3.3.2	Saponification value (SV)	35
3.3.3	Acid value	35
3.3.4	Other characterizations	42
4	Chapter Four: Result And Discussion	43
4.1	Result	44
4.2	Discussion	46
5	Chapter Fives: Conclusion And Recommendation	47
5.1	Conclusion	48
5.2	Recommendation	49
6	References	50

List of Figures

Figure	Name	Page
2.1	Comparison of dietary fats	29
3.2	The clay of preparation	37
3.3	Membranes vacuum filtration unit (Buchner flask, and Buchner funnel, vacuum pump)	39
3.4	Lovibondtintometer instrument (PF Xi-950) serial number (100744)	40
4.1	Bleach ability of cell (1 inch)	44
4.2	Bleach ability of cell (5.25 inch)	45
4.3	The result of oil	45

List of Tables

Table	Name	Page
2.1	Nutritional content	28
2.3	Comparative properties of common cooking fats (per 100 g)	30
4.1	The result of bleach ability refined peanut oil (cell 1 inch)	44
4.2	The result of bleach ability refined peanut oil (cell 5.25 inch)	45

ABSTRACT

The properties of fuller earth had made it valuable in many industrial applications. In general, chemically activated betonies and other activations of betonies may be used as adsorbents in the bleaching of edible oils and other materials.

In this research, crude fuller earth samples obtained from the Blue Nile beach near the Ministry of Energy and Mining was treated by milling, washing, purification and drying. The pretreated samples were then activated with 98% concentrated sulfuric acid and then utilized to bleach a peanut oil. It was found that the efficiency of bleaching was at 56.75% as compared with that of a non-activated fuller earth with 54.05% bleaching efficiency. Based on this result, it was found that local fuller earth can be utilized for bleaching vegetable oils when chemically activated.

ملخص البحث

ان خصائص الارض جعلت للطين قيمة في العديد من التطبيقات الصناعية بصورة عامة، فإن التنشيط الكيميائي للبتونيت او التنشيط بطرق اخرى للبتونيت يمكن استخدامه كمادة ماصة في ازالة اللون من الزيوت النباتية والمعدنية وغيرها من الزيوت(التبييض).

في هذا البحث تم الحصول على العينات من شاطئ النيل الازرق بالقرب من وزارة الطاقة والتعدين وتمت معالجة الخام بالطحن والغسل وكذلك تنقيته وتجفيفه.

تم تنشيط العينات بتركيز ٩٨% من حمض الكبريتيك ثم استخدمت في تبيض زيت الفول السوداني.

فقد وجد ان كفاءة التبيض ٥٦.٧٥% مقارنة مع عينة غير منشطة ٥٤.٠٥% كفاءة تبيضها.

استنادا الى هذه النتيجة تبين ان الطين المحلي يمكن استخدامه لتبيض الزيوت النباتية والمعدنية بعد تنشيطها.